



PALOPAQUE™

Flat Opaque PVC Sheet



CONSTRUCTION



FABRICATION



ADVERTISING



Overview

PALOPAQUE is a flat UV-stabilized PVC sheet, with over 40 years of manufacturing experience that is reflected in its high quality. Easily formed and fabricated, PALOPAQUE is ideal for a wide variety of applications.

PALOPAQUE makes an excellent printing substrate for the advertising and signage industries and is suitable for digital or traditional printing.

With its high chemical resistance, PALOPAQUE is highly suitable for industrial applications. Break-through HYG technology adds active sanitation action for hospitals, clinics and laboratories.

Main Benefits

- Excellent chemical resistance
- High impact strength
- Easily fabricated and formed
- Highest fire rating, self-extinguishing
- Glossy, Matte Hair-Cell or surfaces
- High electrical and thermal insulation
- Easy fabrication
- Non toxic
- PALOPAQUE HYG: Active hygiene



Typical Applications

- Wall cladding
- Advertising and signage
- Chemical process industries
- Chemically resistant Signage
- Sterile surfaces in laboratories
- Clinics and hospitals
- Food industry
- Air vents



www.palram.com



PALOPAQUE™ Product Range

Type	Description
PALOPAQUE™	Standard UV stabilized sheet for general purpose and thermoforming applications. *Increased UV resistance is available upon special request
PALOPAQUE™ HYG	Hygienic panels with active antimicrobial action, effectively eliminating a wide range of harmful microbes.

Standard Dimensions

Width x Length (mm)	Thickness (mm)
1220 x 2440	1 to 15
1000 x 2000	1 to 10
1500 x 3000	1 to 6
2000 x 3000	1 to 4

* Custom dimensions are available, subject to minimum quantity.

Surface Finishes

PALOPAQUE is offered with glossy smooth finish on both sides as standard. Matte and Hair-Cell finishes on one side are optional.

Standard Colors*

White	Light Grey RAL 7040**	Dark Grey RAL 7015**	Metallic Grey RAL 9022**
-------	--------------------------	-------------------------	-----------------------------

* Custom colors are available, subject to minimum quantity.

** Indicated RAL designations are closest match.

Fabrication Tips

PALOPAQUE can be easily fabricated using various techniques. Below are general recommendations for some of them.

Sawing	Machining	Thermoforming	Drilling	Bonding	Welding
For both band and circular saws use blades with a minimum tooth set, and about 8 to 10 teeth per inch. Prevent overheating by feeding slowly.	Use low machining speeds for turning and shaping, and assure free removal of machining chips.	Between 130°C and 170°C PALOPAQUE sheets become formable and can then be formed, press molded or blow formed.	Use conventional drills, but be certain to remove free drill chips in order to avoid overheating of the sheet. Also, use slow rate of penetration.	PALOPAQUE sheets can be bonded with conventional solvent based PVC adhesives.	PALOPAQUE extruded PVC sheets can be welded by hot-air welding process conventionally used for PVC.



PALRAM H.Q.
Tel: +972.4.8459.900
Fax: +972.4.8444.980
palram@palram.com

PALRAM EUROPE LTD.
Tel: +44.1302.380776
Fax: +44.1302.380788
sales.europe@palram.com

PALRAM AMERICAS
Tel: 610.285.9918
Fax: 610.285.9928
palramamericas@palram.com



61272 - 09/2011

In as much as PALRAM Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any PALRAM Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. PALRAM Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local PALRAM Industries supplier to ensure that you have obtained the most up to date information.

©1998 PALRAM Industries Ltd. | PALOPAQUE is a trademark of PALRAM Industries Ltd.

Typical Physical Properties

Property	Method*	Conditions	Units	Value
Density	D-792		g/cm ³	1.4
Heat deflection temperature (H.D.T)	D-648	Load: 1.82MPa	°C	65 - 68
Service Temperature			°C	-10 to +50
Thermal conductivity	C-177		W/m K	0.15
Coefficient of linear thermal expansion	D-696		cm/cm °C	6.7 x 10 ⁻⁵
Rockwell hardness	D-785		R Scale	97R
Tensile strength at yield	D-638	10 mm/min	MPa	50
Tensile strength at break	D-638	10 mm/min	MPa	45
Elongation at yield	D-638	10 mm/min	%	3
Elongation at break	D-638	10 mm/min	%	>80
Tensile modulus of elasticity	D-638	1 mm/min	MPa	2,900
Flexural strength	D-790	1.3 mm/min	MPa	80
Flexural modulus	D-790	1.3 mm/min	MPa	2,700
Impact falling weight	ISO 6603/1 E50	3 mm sheet	J	95

* ASTM except where noted otherwise

Resistance to Chemicals

Excellent resistance to... Mineral acids, alkalis, plating solutions, paper making chemicals, pickling solutions, other inorganic solutions and fumes thereof.

Good resistance to... Alcohols, aliphatic hydrocarbons, glycols, amines, phenols.

Not recommended to contact... ketones, chlorinated solvents, aromatic hydrocarbons, some esters and ethers.

*For more information please refer to "Chemical Resistance of PVC Products" available at www.palram.com or with your PALRAM distributor.

Flammability

PALOPAQUE is self-extinguishing and complies with the most demanding international fire resistance standards defined in the field of plastics, as shown in the attached table.

Standard	Classification*
EN 13501	B, s3, d0
DIN 4102	B-1
BS 476/7	Class 1
NSP 92501,5	M-1
ASTM E-84	Class A

* Depends on thickness

